# DuploCOLL® CPT 9630

Art. No. 11 03 48

## Pressure-sensitive adhesive film made of pure acrylic for lasting, transparent adhesive bonding

Product construction							
	Name	Colour	Thickness [mm]				
Liner	Polyethylene film	white	approx. 0,11 – 0,13				
Adhesive	Pure acrylic		approx. 2,96 – 3,04				
		Total thickness:	approx. 3,07 – 3,17				

## **Product advantages**

- Clear bond due to highly transparent adhesive formulation: the light refraction index of DuploCOLL® CPT 9630 is similar to that
  of glass.
- High stretchable and at the same time a high inner strength give DuploCOLL® CPT 9630 an excellent resiliency within the bond
- · Good initial tack, lasting ultimate bonding strength
- · Good sealing, absorbing and insulating properties
- Excellent stress-absorber
- Particularly versatile, also suitable for uneven surfaces
- Highly split-resistant
- Resistant to chemicals and softeners
- Suitable for long-term use, resistant to ageing and UV radiation
- · Available as perfectly fitting die-cut parts in many shapes, versions and different sizes
- By the technology to seal the edges of the adhesive tape, these become dry after adhesion and resistant against external influences.

### Main application fields

- Bonds where maximum transparency is of central importance, for example in shower cubicles made of glass, at solar collectors and for illuminated advertising signs
- Metal-glass-connections in facade construction and apparatus engineering, as well as in the furniture industry
- Invisible bonding of different materials such as wood, aluminium, plastics, ceramics and glass

Specific technical data*	
Temperature range	-40 °C to +150 °C** (up to +200 °C at short term)
Peel test – floating roller method on glass in accordance with DIN EN 1464 after 24 hours storage at +23 °C +/- 2 °C, V = 300 mm/min	60 N/25 mm
Light transmission	> 80 % in the visible light scope



<sup>\*</sup> Specific test results, statistically not approved.

<sup>\*\*</sup> Reached temperature in a rising heat test according to the internal test method PM-211 following DIN EN 1943 at 0,5 kg strength, beginning at 30 °C, increasing of temperature every 30 minutes by 10 °C.

## DuploCOLL® CPT 9630

Art. No. 11 03 48

## Pressure-sensitive adhesive film made of pure acrylic for lasting, transparent adhesive bonding

Technical Data	
Peel test – floating roller method on steel in accordance with DIN EN 1464 after 24 hours storage at +23 °C +/- 2 °C, v = 300 mm/min	110 N/25 mm
Dynamic shear strength on steel in accordance with internal test method VAR-153001*** after 24 hours storage at +23 °C +/- 2 °C	95 N/625 mm²
Static shear strength on steel on accordance with DIN EN 1943 after 24 hours storage at + 23 °C +/- 2°C	15 N/625 mm²

<sup>\*\*\*</sup>Internal test methods are delivered on request

Application	
Recommended application temperature	18 °C to 35 °C
Application guidelines	www.lohmann-tapes.com

#### **Storage**

Adhesive tapes should be stored at room temperature and normal humidity (50-70 %). The storage stability is 2 years after delivery.

Product presentation					
Converted product	Rolls				
Width [mm]	≥6				
Length [m]	12				
Max. log width: 430 mm	Other dimensions, die-cuts and sheets on request.				

For mechanical mounting of this adhesive tape we also offer a wide range of application devices.

#### **IMPORTANT NOTE**

The physical characteristics contained in this data sheet represent typical or average values. All application related statements, information and recommendations herein are given to the best of our knowledge and practical experience. Many factors beyond our control and uniquely within buyer's knowledge and control can affect the use and performance of our tape in a particular application. EXCEPT AS EXPRESSIVELY AGREED IN WRITING WE DO NOT TAKE OVER ANY WARRANTY OR LIABILITY FOR THE SUITABILITY OR USABILITY OF OUR TAPES FOR CERTAIN PURPOSES AND APPLICATIONS RESULTING FROM BUYER'S SPECIAL USAGE OF THE TAPES. EXCEPT WHERE PROVIDED BY MANDATORY LEGAL PROVISIONS, WE WILL NOT BE LIABLE FOR ANY DIRECT OR INDIRECT MATERIAL OR IMMATERIAL LOSSES OR DAMAGES ARISING FROM THE USAGE OR APPLICATION OF OUR TAPES. Solely the buyer is responsible for determining the suitability of the specific tape for its use in connection with his method of application. Please consult our Technical Applications Department for specific advice.

Date of issue: November 2019

Lohmann GmbH & Co. KG Irlicher Strasse 55 56567 Neuwied Germany

Phone: + 49 (0) 26 31 34 - 0
Fax: + 49 (0) 26 31 34 - 6661
E-mail: info@lohmann-tapes.com

